

Cement Based, High Strength, Flexible Tile Adhesive Mortar

Cement based, polymer-added, high strength, non-slip, C2TES2 class, flexible tile adhesive mortar, developed with additional features, with extended open time.

Advantages

- With S2 class flexibility, it is resistant to surface tensions caused by sudden temperature changes,
- High adhesion strength,
- Saving time and labor with long working time.
- Suitable for pool tiling applications

Field of Application

It can be used indoors and outdoors to apply coating materials such as ceramic natural stone, travertine, decorative brick, granite, porcelain ceramic, clinker, cotto on surfaces such as plaster and screed, horizontally and vertically.

Technical Data

Water Mixing Ratio 5,50 – 6,00 liters water / 25 kg Yapbond® CA Superflex	Reaction to Fire A2	Slip ≤ 0,50 mm	Consumption 4,00 – 6,00 kg/m ² Yapbond® CA S.Flex	Open Time Tensile Adhesion Strength ≥ 0,50 N/mm ²
Initial Adhesion Strength ≥ 1,00 N/mm ²	Post Water-immersing Adhesion Strength ≥ 1,00 N/mm ²	Post freeze-melt cycle Adhesion Strength ≥ 1,00 N/mm ²	Post Heat-ageing Adhesion Strength ≥ 1,00 N/mm ²	Horizontal alteration ≥ 2,50 mm

Pre-application Surface Preparation

Care should be taken to ensure that the surface is clean, dry, and solid. The surface to be applied should be cleaned of residues such as dust, dirt, mold oil, slag, paint that prevent adhesion. Sub-surfaces that are not strong enough to support themselves, such as cracked plasters, weak surfaces, mortar, and cement residues should be scraped from the surface. Plasters thinner than 3 mm on the application surface should be scraped off and completely cleaned from the surface. If there are defects and cracks on the surface to be treated, they should be corrected with YAPBUILT® series repair mortars at least 24 hours before. Before application, the surface should be primed with suitable YAPBOND® series primers, depending on the absorbency of the surface. Before applying on exposed concrete surfaces, the surface should be primed with YAPBOND® GYPSOPLAST to increase the adhesion strength. In ceramics-on-ceramic applications, existing ceramics must be primed with YAPBOND® PRIMER ULTRA. Dusty surfaces behind ceramics should be moistened and wiped. Porous surfaces should be soaked and waited until the water layer disappears so that the surface remains moist.

Application Method

Into approximately 5.50 – 6.00 liters of clean water, 25 kg of YAPBOND® CA SUPER FLEX should be added slowly. It should be mixed until a homogeneous mixture is obtained. The mortar should be rested for 3 – 5 minutes to mature. It should be mixed again for 1 – 2 minutes before starting the application. The mortar should be applied, and its thickness should be adjusted with a threaded steel trowel. The thread size of the trowel should be determined according to the size of the ceramic to be laid and the smoothness of the surface to be applied. In ceramics larger than 500 cm², mortar should be applied both on the surface to be applied and on the back of the ceramic. For good adhesion, air must be expelled by applying force with the help of a rubber hammer. The carded mortar should be glued within a maximum of 20 - 25 minutes. In applications exceeding this period, bonding should not be done on the mortar and the mortar should be scraped from the surface. The prepared mortar should be consumed within 3 hours.

Cement Based, High Strength, Flexible Tile Adhesive Mortar

Post-application Care and Suggestions

The product must be used within expiry date. Expired or crusted mortar in the container should never be used. Tiles adhered with YAPBOND® CA SUPER FLEX should be avoided from direct contact with water for at least 24 hours. It should be protected from freezing and strong sunlight until 5-7 days later. Tile grout should be applied at least 24 hours after ceramic bonding applications to the floor. Floors can be opened to light pedestrian traffic after 24 hours. During and after application, the surface should be protected from air currents. In hot weather, the mortar should be prevented from being exposed to direct sunlight and the mixture should be made with water with the temperature at room conditions. It should not be applied in rainy weather, and the applied surface should be protected from rain for 24 hours. During the application, the surface and ambient temperature should be between +5°C and +35°C. This product is not applied on metal surfaces, wooden floors, exposed concrete, drywall walls. Since it is cement-based, do not breathe the dust, and avoid contact with the skin and eyes. After the applications, hands and application tools should be washed with plenty of water. Surfaces should be cleaned with a damp cloth.

Storage and Shelf Life

It should be stored in a clean, dry and moisture-free environment between +5 °C and +35 °C, away from direct sunlight. It must be protected against water, frost and severe weather. It should be stored in stacks of no more than 10 layers. Provided that the specified storage conditions are complied with, the storage life is a maximum of 12 months from the date of manufacture.

Safety Precaution Information

First, all necessary Occupational Health and Safety measures should be taken in the areas where the application will be done, and the procedures should be carried out by people who have technical knowledge and equipment. Occupational Health and Safety instructions must be followed in all applications. In accordance with the Occupational Health and Safety instructions, it is obligatory to use all occupational safety equipment such as work clothes, protective gloves/goggles/masks during the application. It is necessary to ventilate the work site. Warehouses and stock areas should not be approached with fire. Contact of the product with skin and eyes should be strictly avoided. In such a case, the area where the product comes into contact should be washed immediately with plenty of water, and medical help should be sought immediately. Food and beverages should also not come into contact with the product. The product should be stored and protected in places away from children. For more information, the Material Safety Data Sheet (MSDS) should be reviewed. In addition, the application of the product should be done by people with sufficient technical knowledge, equipment, and experience. The responsibility in this regard belongs exclusively to the user.

Legal Responsibility

All information provided in this information sheet is advisory only. All products should be used by people with technical knowledge and suitable equipment, considering the recommendations. YAPKİM Yapı Kimya San. A.S. cannot be held responsible for any consequences that may occur during or after usage. This document is valid until a new one is issued and invalidates the old editions. YAPKİM Yapı Kimya San. A.S. may make changes in the content of the product. It is imperative to take safety precautions during product use. These measures are not just those listed above, and it is the sole responsibility of the user to take all security measures.

Technical Data Sheet
TDS.BOND.007
Edited:18.07.2023
Revision No.:001

