

Cement Based, Sulphate Resistant Structural Repair Mortar

Cement based, single component, polymer-modified, high-performance, sulphate resistant, R4 class, thixotropic structural repair mortar.

Advantages

- Offers high adhesion strength
- Can be applied up to a thickness of 5 - 20 mm
- Thixotropic, does not sag in vertical applications
- Provides water impermeability before waterproofing applications and surface leveling with high strength chamfer application
- Allows repair of concrete structural elements in both vertical and horizontal directions

Areas of Use

Used on underground, above ground, underwater floors on the interior and exterior facades of all buildings; for chamfer application, repair, surface leveling before waterproofing or final coating; for the repair of concrete and reinforcement damaged by abrasion of reinforcement bars.

Technical Information

Application Thickness
5 - 20 mm

Application Thickness In A Single Coat

Public Works Pos. Number
10.300.2071

Concrete Bonding Strength (28 days)
 $\geq 2.00 \text{ N/mm}^2$

Compression Strength (28 days) $\geq 45.00 \text{ N/mm}^2$

Application Period
60 minutes

Capillary Water Absorption
 $\leq 0.50 \text{ kg.m}^{-2}.\text{h}^{-0.5}$

Surface Preparation Before Application

Concrete surfaces:

Ensure that the surface is clean, dry and free of mold oils. Check the floor with the help of a hammer for the detection of soils with low adherence. Break off weak parts from the floor and leave open corners at the edges of the area to be repaired. Completely uncover rusty reinforcement bars. Always moisturize the surface and saturate it with water on very hot and windy weather before the application.

Reinforcement bars:

Remove rust from the iron with a steel wire brush and remove the dust. Interrupt the contact of the reinforcement bars with the concrete and apply at least 2 coats of anti-corrosion and binder coating primer using a brush. Perform the next application while the material is still wet, i.e. wet-on-wet.

Method of Application

Add an average of 4.25 - 5.00 liters of clean water to a 25 kg bag of YAPBUILT RM S60. Mix YAPBUILT RM S60 with a trowel or a low speed hand mixer until it becomes homogeneous. Allow the mixture to stand for 2 minutes before application.

Apply YAPBUILT RM S60 evenly over the entire surface with a steel trowel. If more than one coat will be applied, wait 3 hours between coats and moisturize the surface before applying the next coat. Total thickness should not exceed 20 mm. Ensure the smoothness of the surface with a plastic trowel or damp sponge. After application, moisturize the surface for 2-3 days.

Do not add water to the hardening mortar.

Cement Based, Sulphate Resistant Structural Repair Mortar

Maintenance and Recommendations After Application

When applying **YAPBUILT RM S60**, if the ambient temperature is below +5°C or above +35°C, wait for suitable temperatures. Do not apply in extremely hot, rainy or windy weather. Do not apply on surfaces that are frozen, melting or in danger of frost within 24 hours. The thickness of single coat application should be max. 10.0 mm. Do not add water and new material to the mixture that has started to cure. Not applicable on plaster, old painted surfaces, gas concrete. Clean the tools and equipment you have used with water after application. **YAPBUILT RM S60** may only be mechanically removed from the surface after it has hardened.

Storage and Shelf Life

Store in a clean, dry environment, free from moisture, between +5°C and +35°C, away from direct sunlight. Protect against water, frost and severe weather conditions. Store in stacks of maximum 10 layers. Storage life is maximum 12 months from the date of production, provided that the storage conditions specified are complied with.

Consumption

An average of 1.80 - 2.0 kg/m² **YAPBUILT RM S60** is used for 1 mm application thickness.

Information on Safety Precautions

First, take all necessary Occupational Health and Safety precautions in the areas for the application and ensure that the operations are carried out by persons with technical knowledge and equipment. Observe occupational Health and Safety instructions in all work carried out. It is mandatory to use all occupational safety equipment such as work clothes, protective gloves/goggles/masks etc. specified in accordance with the Occupational Health and Safety instructions during the application. The working area needs to be ventilated. Do not approach warehouses and storage areas with fire. Avoid contact of the product with skin and eyes, immediately wash the area of contact with plenty of water and seek medical advice immediately in such a case. Also, prevent contact of food and beverages with the product. Store and protect away from children. See Material Safety Data Sheet (**MSDS**) for further information. Also, the application of the product should be carried out by persons with adequate technical knowledge, equipment and experience. The user is solely responsible for this.

Responsibility

All information provided in this data sheet is intended as advice. All products should be used by persons with technical knowledge and equipment, observing the recommendations. **YAPKİM Yapı Kimya San. A.Ş.** cannot be held responsible for any consequences that may occur during or after any use. This document is valid until a new version is issued and supersedes all previous versions. **YAPKİM Yapı Kimya San. A.Ş.** may make changes in the nature of the product. Safety precautions must be taken during the use of the product. These measures are not limited to those listed above as examples, and it is the sole responsibility of the user to take all security measures.

Technical Data Sheet
TDS.BUILD.007
Issued: 18.07.2023
Revision No: 001

